

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



10/528220



(43) International Publication Date  
22 April 2004 (22.04.2004)

PCT

(10) International Publication Number  
WO 2004/033222 A2

(51) International Patent Classification<sup>7</sup>: B41M 5/00

(21) International Application Number:  
PCT/US2003/031604

(22) International Filing Date: 6 October 2003 (06.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/416,999 8 October 2002 (08.10.2002) US

(71) Applicant (for all designated States except US): SCIENTIFIC GAMES, INC. [US/US]; 1500 Bluegrass Lakes Parkway, Alpharetta, GA 30004 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): TEVIS, Mark, C. [US/US]; 5870 Briar Court, Cumming, GA 30040 (US). DOWNING, Ken [US/US]; 6680 Stillmeadow Drive, Cumming, GA 30040 (US).

(74) Agents: NEEDLE, William, H. et al.; Needle & Rosenberg, P.C., Suite 100, 999 Peachtree Street, Atlanta, GA 30309-3915 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHODS FOR APPLYING COATING COMPOSITIONS TO AN ARTICLE AND ARTICLES PRODUCED THEREOF

(57) Abstract: Described herein are methods for applying multiple layers of a composition to an article. Also presented are articles produced by the methods described herein.

WO 2004/033222 A2

# **METHODS FOR APPLYING COATING COMPOSITIONS TO AN ARTICLE AND ARTICLES PRODUCED THEREOF**

## **CROSS-REFERENCE TO RELATED APPLICATION**

5

This application claims the benefit of U.S. Provisional Patent Application Serial Number 60/416,999, filed on October 8, 2002. This provisional patent application is herein incorporated by this reference in its entirety for all of its teachings.

10

## **SUMMARY OF THE INVENTION**

Described herein are methods for applying multiple layers of a composition to an article. Also presented are articles produced by the methods described herein.

It is desirable to be able to produce an article having multiple layers in an efficient manner during manufacturing. It is also desirable to produce articles that have improved mechanical properties and improved security features, such as graphic adhesion, improved backside wick protection and improved resistance to image ink alteration and migration. The methods described herein satisfy this current need in the art.

Additional advantages of the invention will be set forth in part in the description that follows, and in part will be obvious from the description, or can be learned by practice of the invention. The advantages of the invention will be realized and attained by means of the elements and combinations particularly pointed out in the appended claims. It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the invention, as claimed.

### **DETAILED DESCRIPTION OF THE INVENTION**

The methods and articles described herein can be understood more readily by reference to the following detailed description of preferred aspects and the Examples included herein.

5           It must be noted that, as used in the specification and the appended claims, the singular forms "a," "an" and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to "an aromatic compound" includes mixtures of aromatic compounds, reference to "a carrier" includes mixtures of two or more such carriers, and the like.

10           Ranges are often expressed herein as from "about" one particular value, and/or to "about" another particular value. When such a range is expressed, another aspect includes from the one particular value and/or to the other particular value. Similarly, when values are expressed as approximations, by use of the antecedent "about," it will be understood that the particular value forms another aspect. It will be further  
15 understood that the endpoints of each of the ranges are significant both in relation to the other endpoint, and independently of the other endpoint.

A weight part of a component, unless specifically stated to the contrary, is based on the weight or mass of one component relative to the weight or mass of a second component. The weight or mass can be expressed in grams, pounds, or any other  
20 acceptable unit of mass. Percentages of components are expressed as percent of the total formula weight.

Throughout this publication, where publications are referenced, the disclosures of these publications in their entireties are hereby incorporated by reference into this application in order to more fully describe the state of the art to which this invention  
25 pertains.

Described herein are methods for applying multiple layers of a coating composition on the outer surface of an article. In one aspect, the method involves

- 5 (a) applying a first composition comprising a first oligomer comprising an energy-curable oligomer to the outer surface of the article to produce a first layer, wherein after the application step (a), a first layer comprising the first oligomer is on the outer surface of the article, and wherein the first layer has an outer surface;
- (b) drying the article produced after step (a);
- 10 (c) applying a second composition comprising a second oligomer comprising an energy-curable oligomer to the outer surface of the first layer to produce a second layer, wherein after the application step (b), the second layer is on the outer surface of the first layer, and wherein the second layer has an outer surface;
- (d) drying the article produced after step (c);
- 15 (e) applying a third composition comprising a third oligomer comprising an energy-curable oligomer to the outer surface of the second layer to produce a third layer, wherein after the application step (d), the third layer is on the outer surface of the second layer; and
- (f) curing the first oligomer, the second oligomer, and the third oligomer.

The first, second and third compositions comprise one or more energy-curable oligomers. The term "oligomer" referred to herein is defined as a substance composed of oligomer molecules. An "oligomer molecule" is defined herein as a molecule of intermediate relative molecular mass, the structure of which is composed of a small plurality of units derived, actually or conceptually, from molecules of lower relative molecular mass. A molecule is regarded as having an intermediate relative molecular mass if it has properties which do vary significantly with the removal of one or a few of the units. If a part or the whole of the molecule has an intermediate relative molecular mass and essentially comprises a small plurality of units derived, actually or conceptually, from molecules of lower relative molecular mass, it can be described as oligomeric, or by oligomer used adjectively.

20

25

The term "energy-curable" refers to a compound that can cross-link or react with another compound when exposed to energy in the form of UV light or energy from an electron beam. Generally, energy-curable compounds contain one or more unsaturated groups including, but not limited to, carbon-carbon double and triple bonds as well as ring systems. The energy-curable compounds useful in the methods described herein can cross-link or react with one another by free radical chemistry or cationic chemistry using techniques known in the art.

In one aspect, the first, second and/or third oligomer is water based. In another aspect, the third oligomer is not water based. The term "water-based," which is also referred to as "water-dilutable," refers to compounds that are miscible or dispersible in water. For example, a water-based oligomer can be part of a composition containing 10% to 50% water and still maintain its integrity. Alternatively, the water-based oligomers used herein in this aspect can be diluted with water and the oligomer still maintains its integrity.

In one aspect, the first oligomer, the second oligomer, and the third oligomer are (1) a polyester or urethane having an acrylate group or (2) a cycloaliphatic diepoxide. Examples of first, second and third oligomers useful herein include, but are not limited to, an epoxy acrylate, a urethane acrylate, a polyester acrylate, an acrylated acrylic, or a cycloaliphatic diepoxide. Specific examples of first oligomer and second oligomer include, but are not limited to, LUX 241, LUX 101, LUX 121, and LUX 399 from Alberdingk-Boley, Inc. and Ucecoat 7770 and Ucecoat 7772 from UCB Chemical. In another aspect, the first and second oligomer has a glass transition temperature of about 50 °C to about 110 °C, and the third oligomer has a glass transition temperature of about -30 °C to about 60 °C.

In one aspect, the first oligomer, the second oligomer, and the third oligomer are different compounds. In another aspect, the first oligomer and the second oligomer are the same compound. In a further aspect, the first oligomer and the third oligomer are the same compound. In another aspect, the second oligomer and the third oligomer are the same compound. In another aspect, the first composition comprises two or more



different first oligomers. Similarly, the second and third compositions can also comprise two or more different second or third oligomers, respectively.

In one aspect, the amount of first oligomer and second oligomer present in the first composition and second composition, respectively, is from 10% to 40%, 15% to 40%, 15% to 35%, 18% to 35% or 20% to 35% by weight of the composition. In another aspect, the amount of third oligomer present in the third composition is from 15% to 50%, 15% to 40%, 15% to 35%, 15% to 30%, 20% to 50%, 20% to 45% or 20% to 40% by weight of the composition.

The first, second and third compositions can optionally contain other components including, but not limited to, a surfactant, a thickener, an absorbent, a pigment or dye, which are commonly used in the art. In another aspect, the third composition also comprises a slip additive, a release additive, or wax. The first, second and third composition can also contain water or a low boiling organic solvent. Examples of low boiling organic solvents include, but are not limited to, alcohols such as ethyl alcohol, normal propyl alcohol, isopropyl alcohol, or butyl alcohol, esters and ketones.

In one aspect, the first composition comprises water, a surfactant, a thickener, a pigment or dye, preferably a black pigment, and a first oligomer comprising a water-based, energy-curable oligomer. In another aspect, the second composition comprises water, a surfactant, a thickener, an absorbent, a pigment or dye, and a second oligomer comprising a water-based, energy-curable oligomer. In another aspect, the third composition comprises a surfactant, a slip additive, a wax and a third oligomer comprising an energy-curable oligomer.

The methods described herein contemplate applying the first, second and third compositions to an article. The term "applying" with respect to any of the compositions described herein refers to any technique known in the art for placing a coating on a substrate. Examples of techniques useful for applying any of the compositions described herein on the article include, but are not limited to, flexography, roto gravure, screen printing, offset, letter press or roll coater. In one aspect, the compositions described herein are applied to the article by flexography.

The term "outer surface" with respect to the article includes the portion of the article that is exposed to air and visible. The term "outer surface" also includes a section of the article that resides just below the exposed, visible surface of the article. For example, when the first composition is applied to the outer surface of the article, some of the first composition can be absorbed by the article so that some of the first composition is below the exposed, visible surface of the article.

The term "outer surface" with respect to the different layers produced by the compositions described herein also refers to the part of the layer produced by the first, second or third composition that is exposed to air and visible as well as the section of the layer below the exposed, visible surface that can absorb any components of the composition. In certain aspects, it is possible that adjacent layers can diffuse into each other. When two layers diffuse into one another at the interface upon curing, this is referred to in the art as "tying together." When two layers diffuse into one another at the interface upon drying, this is referred to in the art as "commingling" or "intermingling."

The thickness of each layer that is applied to the article can vary produced by the methods described herein is from 0.1 mil to 0.7 mil, 0.1 mil to 0.6 mil, depending upon the technique that is used to apply the composition as well as the end-use of the article. In one aspect, the wet thickness of any layer is from 1 mil to 0.5 mil, 0.1 mil to 0.4 mil or 0.1 mil to 0.3 mil, and preferably 0.3 layer. In another aspect, the first composition has a coating weight of 1.0# to 4# per thousand square feet, the second composition has a coating weight of 1.5# to 5# per thousand square feet, and the third composition has a coating weight of 1.0# to 4# per thousand square feet.

The methods described herein also contemplate applying two or more different first compositions or second compositions to the outer surface of the article. For example, a first composition can be applied to the outer surface of the article. Once this composition is applied to the article, this composition will produce a first layer of first oligomer having an outer surface. A second first composition can then be applied to the outer surface of the first composition to produce a second first layer. Depending

upon the application, several layers of first and second oligomer can be applied to the article.

The methods described herein involve performing a drying step (1) after the first composition is applied to the article and (2) after the second composition is applied to the outer surface of the first layer. The drying steps (b) and (d) generally involve drying the first and second layers so that these layers are dry to the touch. In one aspect, drying steps (b) and (d) are performed by exposing the article with the first layer or second layer to a gas fired or electrically fired dryer coupled with a large flow of air volume. In one aspect, the temperature of the drying steps is from 230 °F to 390 °F. The source of the large volume of air flow can be any blower known in the art. In one aspect, the blower can be a separate mechanical device or it can be part of a forced air dryer. Alternatively, the drying step can be performed by an IR dryer with no large volume of air flow.

In another aspect, the drying steps (b) and (d) can also encompass partial curing of the first and/or second oligomers. In one aspect, when no water is present in the first and second compositions, the first and second oligomers present in the first and second layers can be partially cured during the drying step by exposing the first and second oligomers to a UV lamp. In one aspect, when the first and/or second oligomer is a cycloaliphatic diepoxide, drying steps (b) and/or (d) is (are) performed by exposing the first and/or second oligomers to a UV lamp.

Not wishing to be bound by theory, it is believed that when drying steps (b) and (d) involve thermal heating in the presence of a large volume of air flow, the first oligomer and second oligomer do not react or cross-link with one another even though some of the first oligomer can diffuse into the second layer and vice versa (*i.e.*, commingle or intermingle). Alternatively, when drying steps (b) and (d) involve exposing the first and second layers to light (*e.g.*, a UV lamp), the first and second oligomers partially react or cross-link (*i.e.*, tie together). When the first and second layers are commingled, intermingled and/or tied together, it is believed that the resultant article will have improved graphic adhesion, improved backside wick protection and improved resistance to image ink alteration or image ink migration by



thermal or chemical means, once the layers are cured. Additionally, after drying steps (b) and (d) are performed, the first and second layers on the article are capable of passing through the press before being cured without tracking or picking, which is another advantage of the methods described herein.

5        After drying step (d), the third composition is applied to the outer surface of the second layer to produce a third layer. After the formation of the third layer, the first, second, and third layers are cured in order to cross-link the first, second and/or third oligomers. The amount of cross-linking amongst the oligomers will vary depending upon the type of oligomer and the mode of curing. In one aspect, the curing step (f) is  
10       performed by using a UV lamp. For example, a "D" bulb can be used to cure the first oligomer present in the first layer, and a "D," "H," or "V" bulb can be used to cure the second oligomer in the second layer. In another aspect, the first, second and third layers can be cured by exposing the layers to an electron beam. In this aspect, the first, second and third oligomers cross-link with one another. The amount of cross-linking  
15       between the different oligomers will depend upon the type of first, second and third oligomer and the amount of commingling, intermingling or tying together that occurs between the different oligomers in the first, second and third layers.

In another aspect, an image ink can be applied to the article. In one aspect, the image ink can be applied to the outer surface of the first and/or second layer after the  
20       first and second layer have been dried in steps (b) and (d), respectively. In one aspect, the image ink is applied to the outer surface of the second layer after the second layer has been dried in step (d) to produce an image comprised of alpha numeric indicia. Once the image ink has been applied to the outer surface of the first or second layer, the resultant image can be dried using the techniques described above and subsequent  
25       layers can be applied over the image. In one aspect, the image ink can be applied to the outer surface of the first or second layer using any method of ink jet printing including, but not limited to, drop on demand or continuous ink jet. In one aspect, the image can occupy a portion of the first or second layer. In this aspect, when a subsequent layer is applied over the image, the subsequent layer can be in contact with the image as well as  
30       the outer surface of the first or second layer.

In one aspect, the image ink is water based or solvent based. In another aspect, the image ink is energy curable. When the image ink is energy curable, it can cross-link or react with the first, second or third oligomer upon cross-linking. The image ink can be most any color, and the color will be determined by the selection of the dye and/or pigment used to prepare the image ink. The image inks disclosed in U.S. patent nos. 6,310,115 and 6,156,110, which are incorporated by reference in their entireties, are useful in the methods described herein.

In one aspect, the sumps containing the first, second and third compositions and the image ink can be maintained at a temperature of 80 °F to 110 °F to maintain proper viscosity and flow. In one aspect, the first and second compositions have a viscosity of 19 seconds to 55 seconds at #2 Zahn ( at 80 °F ) for a flexography application. In another aspect, the third composition have a viscosity range of 18 to 40 seconds at #2 Zahn ( at 80 °F ) for a flexography application. Other application methods would require other viscosity ranges that are readily determinable.

The methods described herein are useful in applying multiple layers of a coating composition to the outer surface of an article. Examples of articles that can be coated with the methods described herein include, but are not limited to, lottery tickets, phone cards and commercial games. In one aspect, when the article is a lottery ticket, the lottery ticket is composed of SBS board stock.

The methods described herein provide numerous advantages over prior art techniques. For example, when the methods described herein are used to coat a game ticket, the play data area is much whiter than the older ticket configuration. The backside wick test results are much improved. Additionally, no bleed detecting dye is necessary in the lower blocking layer because of the improved barrier properties. Overall, the ticket opacity is much improved.

The invention has been described in detail with particular reference to preferred aspects thereof, but it will be understood that variations and modifications can be affected without departing from the scope and spirit of the invention.

### EXAMPLES

The following example is put forth so as to provide those of ordinary skill in the art with a complete disclosure and description of how the compositions, articles, and/or methods claimed herein are made and evaluated, and are intended to be purely  
5 exemplary and are not intended to limit the scope of what the inventors regard as their invention. Efforts have been made to ensure accuracy with respect to numbers (e.g., amounts, temperature, etc.), but some errors and deviations should be accounted for. Unless indicated otherwise, parts are parts by weight, temperature is in °C or is at ambient temperature, and pressure is at or near atmospheric. The term "line" refers to  
10 lines per inch. The term "BCM" is billion cubic microns, which represents the cell volume of the anilox roller and is a major determinant of the volume of composition that is applied to the card.

A twenty one unit flexo press with an ESI EZCure 1 electron beam unit running at 125 KV was used to coat game cards. A dosage of 2.5 MRAD was used to cure the  
15 three compositions all at once. A dosage of from 2.5 to 4.5 MRAD was acceptable, depending on the total thickness of the three compositions. When tested on the twenty-one unit flexo press, the following anilox configurations and volumes were acceptable;

1<sup>st</sup> composition 165 line anilox, 13 BCM volume  
2<sup>nd</sup> composition 120 line anilox, 15 BCM volume  
20 3<sup>rd</sup> composition 165 line anilox, 13 BCM volume

The above configurations use only one "hit" (*i.e.*, layer) of each composition. When two "hits" of a composition were applied, the second hit had the following anilox configurations;

25

1<sup>st</sup> composition 200 line anilox, 10 BCM volume  
2<sup>nd</sup> composition 165 line anilox, 13 BCM volume  
3<sup>rd</sup> composition, only one hit of the 3<sup>rd</sup> composition was applied

30 When two hits of a composition are applied to the card, the first hit contained a higher

volume of composition when compared to the volume of the second hit.

What is claimed:

1. A method for applying a coating composition to an article having an outer surface, comprising
  - (a) applying a first composition comprising a first oligomer comprising an energy-curable oligomer to the outer surface of the article to produce a first layer, wherein after the application step (a), a first layer comprising the first oligomer is on the outer surface of the article, and wherein the first layer has an outer surface;
  - (b) drying the article produced after step (a);
  - (c) applying a second composition comprising a second oligomer comprising an energy-curable oligomer to the outer surface of the first layer to produce a second layer, wherein after the application step (b), the second layer is on the outer surface of the first layer, and wherein the second layer has an outer surface;
  - (d) drying the article produced after step (c);
  - (e) applying a third composition comprising a third oligomer comprising an energy-curable oligomer to the outer surface of the second layer to produce a third layer, wherein after the application step (d), the third layer is on the outer surface of the second layer; and
  - (f) curing the first oligomer, the second oligomer, and the third oligomer.
2. The method of Claim 1, wherein the composition in steps (a), (c) and (e) is applied by flexography, roto gravure, screen printing, offset, letter press or roll coater.
3. The method of Claim 1, wherein the composition in steps (a), (c) and (e) is applied by flexography.
4. The method of Claim 1, wherein the first oligomer and second oligomer are water based.



5. The method of Claim 1, wherein the first oligomer, the second oligomer and the third oligomer comprises an epoxy acrylate, a urethane acrylate, a polyester acrylate, an acrylated acrylic, a cycloaliphatic diepoxide or a combination thereof.
6. The method of Claim 1, wherein the first oligomer, the second oligomer and the third oligomer comprises (1) a polyester or urethane having an acrylate group or (2) a cycloaliphatic diepoxide.
7. The method of Claim 1, wherein the first oligomer and second oligomer is from 10% to 40% by weight of the first composition and second composition.
8. The method of Claim 1, wherein the third oligomer is from 15% to 50% by weight of the third composition.
9. The method of Claim 1, wherein the third oligomer is not water based.
10. The method of Claim 1, wherein the first composition comprises water, a surfactant, a thickener, a pigment or dye, and a first oligomer comprising a water-based, energy-curable oligomer.
11. The method of Claim 1, wherein the second composition comprises water, a surfactant, a thickener, an absorbent, a pigment or dye, and a second oligomer comprising a water-based, energy-curable oligomer.
12. The method of Claim 1, wherein the third composition comprises a surfactant, a slip additive, a release additive, a wax and a third oligomer comprising an energy-curable oligomer.
13. The method of Claim 1, wherein the drying steps (b) and (d) are performed by a dryer at a temperature of from 230 °F to 390 °F in the presence of a large flow of air volume.
14. The method of Claim 1, wherein when drying steps (b) and/or (d) are performed by an UV lamp, the first composition and/or the second composition is cured.

15. The method of Claim 1, wherein the curing step (f) is performed by exposing the article produced after step (d) to an electron beam or UV lamp.
16. The method of Claim 1, wherein after step (b) and prior to step (c), applying an image ink to the outer surface of the first layer to produce an image.
17. The method of Claim 1, wherein after step (d) and prior to step (e), applying an image ink to the outer surface of the second layer to produce an image.
18. The method of Claim 16, wherein the image ink is water based.
19. The method of Claim 1, wherein the article is a lottery ticket, phone card or commercial game.
20. The method of Claim 1, wherein the article is a lottery ticket.
21. A method for applying a coating composition to a lottery ticket having an outer surface, comprising
  - (a) applying a first composition comprising a first oligomer comprising an energy-curable, water-based oligomer to the outer surface of the article to produce a first layer, wherein after the application step (a), a first layer comprising the first oligomer is on the outer surface of the article, and wherein the first layer has an outer surface;
  - (b) drying the article produced after step (a) at a temperature of from 230 °F to 390 °F in the presence of a large flow of air volume;
  - (c) applying a second composition comprising a second oligomer comprising an energy-curable, water-based oligomer to the outer surface of the first layer to produce a second layer, wherein after the application step (b), the second layer is on the outer surface of the first layer, and wherein the second layer has an outer surface;
  - (d) drying the article produced after step (c) at a temperature of from 230 °F to 390 °F in the presence of a large flow of air volume;

- (e) applying an image ink to the outer surface of the second layer to produce an image;
- (f) drying the article produced after step (e);
- (g) applying a third composition comprising a third oligomer comprising an energy-curable oligomer over the image and the outer surface of the second layer to produce a third layer; and
- (h) curing the first oligomer, the second oligomer, and the third oligomer with an electron beam,

wherein the first oligomer, the second oligomer and/or the third oligomer comprises a polyester acrylate, urethane acrylate, an epoxy acrylate or a combination thereof.

- 22. An article produced by the method of Claim 1.
- 23. An article produced by the method of Claim 21.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



10/528220



(43) International Publication Date  
22 April 2004 (22.04.2004)

PCT

(10) International Publication Number  
WO 2004/033222 A3

(51) International Patent Classification<sup>7</sup>: B05D 7/00, 3/06

(21) International Application Number:  
PCT/US2003/031604

(22) International Filing Date: 6 October 2003 (06.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/416,999 8 October 2002 (08.10.2002) US

(71) Applicant (for all designated States except US): SCIENTIFIC GAMES, INC. [US/US]; 1500 Bluegrass Lakes Parkway, Alpharetta, GA 30004 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): TEVIS, Mark, C. [US/US]; 5870 Briar Court, Cumming, GA 30040 (US).  
DOWNING, Ken [US/US]; 6680 Stillmeadow Drive, Cumming, GA 30040 (US).

(74) Agents: NEEDLE, William, H. et al.; Needle & Rosenberg, P.C., Suite 100, 999 Peachtree Street, Atlanta, GA 30309-3915 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:  
23 September 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHODS FOR APPLYING COATING COMPOSITIONS TO AN ARTICLE AND ARTICLES PRODUCED THEREOF

(57) Abstract: Described herein are methods for applying multiple layers of a composition to an article. Also presented are articles produced by the methods described herein.

WO 2004/033222 A3

# INTERNATIONAL SEARCH REPORT

International Application No.  
13/31604

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 B05D7/00 B05D3/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 B05D B41M A63F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 149 712 A (TARKETT SOMMER S A) 31 October 2001 (2001-10-31)  paragraphs '0022!, '0023!, '0026!, '0027!, '0031!, '0036!, '0044! -----	1-3,5,6, 14,15, 21-23
X	EP 0 983 801 A (DUKEPLANNING & CO INC) 8 March 2000 (2000-03-08) paragraphs '0061!, '0065!, '0066!, '0069!, '0076! claims 1,2,4 -----	1
X	US 5 401 541 A (HODNETT III WILLIAM P) 28 March 1995 (1995-03-28) claims 1,8 -----  -/--	1,14,15

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*G\* document member of the same patent family

Date of the actual completion of the international search

5 August 2004

Date of mailing of the international search report

13/08/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Slembrouck, I



## INTERNATIONAL SEARCH REPORT

International Application No

T, ... 03/31604

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 914 875 A (KANSAI PAINT CO LTD) 12 May 1999 (1999-05-12) paragraphs '0024!, '0026!, '0048!, '0049!, '0054!, '0055!, '0063!, '0080!, '0088! claims 1,18,33 -----	1
A	GB 642 892 A (WESTERN ELECTRIC CO) 13 September 1950 (1950-09-13) page 2, line 23 - line 46 -----	1,21-23
A	US 6 379 742 B1 (BEHM WILLIAM F ET AL) 30 April 2002 (2002-04-30) column 12, line 34 - line 37 column 12, line 51 - line 53 tables 1,2 column 14, line 16 - line 40 column 14, line 64 - line 66 column 15, line 10 - line 28 column 47, line 27 - line 33 -----	1,21-23

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

US 03/31604

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1149712	A	31-10-2001	EP 1149712 A1	31-10-2001
			AT 257092 T	15-01-2004
			AU 1121201 A	07-11-2001
			WO 0181102 A1	01-11-2001
			BG 107280 A	31-07-2003
			CA 2406991 A1	01-11-2001
			CZ 20023350 A3	16-04-2003
			DE 60007560 D1	05-02-2004
			EP 1276621 A1	22-01-2003
			ES 2210007 T3	01-07-2004
			SK 14672002 A3	03-06-2003
EP 0983801	A	08-03-2000	JP 2000070845 A	07-03-2000
			JP 2001046962 A	20-02-2001
			CA 2281360 A1	04-03-2000
			EP 0983801 A2	08-03-2000
			US 6312765 B1	06-11-2001
			US 2002009552 A1	24-01-2002
US 5401541	A	28-03-1995	US 5254395 A	19-10-1993
			US 5114783 A	19-05-1992
			EP 0439967 A1	07-08-1991
EP 0914875	A	12-05-1999	JP 11128831 A	18-05-1999
			JP 11128832 A	18-05-1999
			JP 11169784 A	29-06-1999
			CA 2252096 A1	28-04-1999
			EP 0914875 A2	12-05-1999
			US 6231984 B1	15-05-2001
GB 642892	A	13-09-1950	NL 67330 C	
US 6379742	B1	30-04-2002	US 5997044 A	07-12-1999
			US 5599046 A	04-02-1997
			US 2004053011 A1	18-03-2004
			AU 2947295 A	15-01-1996
			WO 9535216 A1	28-12-1995

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☒ **OTHER:** hole - punched over text

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**